



**SHERWIN-WILLIAMS.**  
Automotive Finishes

# Introducing:


## AWX™ Waterborne Basecoat System 3.5 VOC



Excellent coverage  
with minimal coats



Simple, compact toner  
line that is easy to mix



Superior color  
match and blending  
properties



Lowest capital  
investment of any  
waterborne system



Quick flash times  
between coats




# AWX™

Compliance without Complication™

# AWX™

Compliance without Complication™

## Great Product Provides Great Results... Sherwin-Williams' AWX Provides Both!



### MIXING



1

AWX™  
Color

+



10%

AWX™ Basecoat  
Reducer 4550001

### OR

(for extreme temperature areas)



1


AWX™  
Color

+




10%-20%

AWX™  
Slow Basecoat  
Reducer 4550002\*



### APPLICATION

- Apply 1-3 medium coats until hiding is achieved.
- 7-9 psi air cap pressure HVLP
- Use a low pressure finesse coat to even out metallic/mica colors for blending: 4-5 psi air cap pressure HVLP.
- Fluid nozzle range: 1.2-1.3 MM
- Film build should be .5-1.0 mils.



### DRYING SCHEDULE

#### Dust Free:

Air Dry – 75°F 5-10 minutes

Venturi – 95°F 2-3 minutes

#### Tape Time:

Air Dry – 75°F 20-30 minutes

Venturi – 95°F 10 minutes

#### Recoat:

Air Dry – 75°F 20-30 minutes

Venturi – 95°F 10 minutes